



NACE SP0198-2010
(formerly RP0198)
Item No. 21084

Standard Practice

Control of Corrosion Under Thermal Insulation and Fireproofing Materials—A Systems Approach

This NACE International standard represents a consensus of those individual members who have reviewed this document, its scope, and provisions. Its acceptance does not in any respect preclude anyone, whether he or she has adopted the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not in conformance with this standard. Nothing contained in this NACE International standard is to be construed as granting any right, by implication or otherwise, to manufacture, sell, or use in connection with any method, apparatus, or product covered by Letters Patent, or as indemnifying or protecting anyone against liability for infringement of Letters Patent. This standard represents minimum requirements and should in no way be interpreted as a restriction on the use of better procedures or materials. Neither is this standard intended to apply in all cases relating to the subject. Unpredictable circumstances may negate the usefulness of this standard in specific instances. NACE International assumes no responsibility for the interpretation or use of this standard by other parties and accepts responsibility for only those official NACE International interpretations issued by NACE International in accordance with its governing procedures and policies which preclude the issuance of interpretations by individual volunteers.

Users of this NACE International standard are responsible for reviewing appropriate health, safety, environmental, and regulatory documents and for determining their applicability in relation to this standard prior to its use. This NACE International standard may not necessarily address all potential health and safety problems or environmental hazards associated with the use of materials, equipment, and/or operations detailed or referred to within this standard. Users of this NACE International standard are also responsible for establishing appropriate health, safety, and environmental protection practices, in consultation with appropriate regulatory authorities if necessary, to achieve compliance with any existing applicable regulatory requirements prior to the use of this standard.

CAUTIONARY NOTICE: NACE International standards are subject to periodic review, and may be revised or withdrawn at any time in accordance with NACE technical committee procedures. NACE International requires that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of initial publication and subsequently from the date of each reaffirmation or revision. The user is cautioned to obtain the latest edition. Purchasers of NACE International standards may receive current information on all standards and other NACE International publications by contacting the NACE International *FirstService* Department, 1440 South Creek Dr., Houston, TX 77084-4906 (telephone +1 281-228-6200).

Revised 2010-6-25
Reaffirmed 2004-3-31
Approved 1998-2-20
NACE International
1440 South Creek Drive
Houston, Texas 77084-4906
+1 281-228-6200

ISBN 1-57590-049-1
©2010, NACE International

Foreword

This NACE standard practice provides the current technology and industry practices for mitigating corrosion under thermal insulation and fireproofing materials, a problem termed *corrosion under insulation (CUI)* in this standard. Because this corrosion problem has many facets and impacts several technologies, a systems approach has been adopted. This standard is intended for use by corrosion-control personnel and others concerned with corrosion under insulation and/or fireproofing of equipment.

This standard is organized into sections by function. Each section was written by specialists in that subject. These specialists are industry representatives from firms producing, specifying, designing, and/or using thermal insulation and fireproofing products on refinery and petrochemical equipment.

This standard was originally prepared in 1998 by NACE Work Group T-5A-30a, "Corrosion Protection Under Insulation," with the assistance of Task Group (TG) T-6H-31, "Coatings for Carbon and Austenitic Stainless Steel Under Insulation," and ASTM⁽¹⁾ Committee C16.40.3, "Corrosion Under Insulation." Work Group T-5A-30a supported NACE TG T-5A-30, "Corrosion Under Thermal Insulation," a component of NACE Unit Committee T-5A, "Corrosion in Chemical Processes." The standard was reaffirmed in 2004 by Specific Technology Group (STG) 36, "Process Industry: Materials Performance in Chemicals." It was revised in 2010 by TG 325, "CUI: Revision of NACE Standard RP0198, The Control of Corrosion Under Thermal Insulation and Fireproofing Materials—A Systems Approach," with the assistance of Technology Exchange Group (TEG) 255X, "Coatings, Thermal-Spray for Corrosion Protection." TG 325 is sponsored by STG 03, "Coatings and Linings, Protective—Immersion and Buried Service," and STG 04, "Coatings and Linings, Protective—Surface Preparation." This standard is issued by NACE International under the auspices of STG 36.

In NACE standards, the terms *shall*, *must*, *should*, and *may* are used in accordance with the definitions of these terms in the *NACE Publications Style Manual*. The terms *shall* and *must* are used to state a requirement, and are considered mandatory. The term *should* is used to state something good and is recommended, but is not considered mandatory. The term *may* is used to state something considered optional.

⁽¹⁾ ASTM International (ASTM), 100 Barr Harbor Dr., West Conshohocken, PA 19428-2959.

**NACE International
Standard Practice**

**Control of Corrosion Under Thermal Insulation and Fireproofing
Materials—A Systems Approach**

Contents

1. General.....	1
2. Corrosion Mechanisms	2
3. Mechanical Design.....	9
4. Protective Coatings	20
5. Insulation, Fireproofing, and Accessory Materials	27
6. Inspection and Maintenance	31
References.....	37
Bibliography	39
FIGURES	
Figure 1: Effect of Temperature on Steel Corrosion in Water.....	4
Figure 2: Typical Vessel Attachments Where Water May Bypass Insulation	11
Figure 3: Attachment to Piping Where Water May Bypass Insulation	12
Figure 4: Vessel Insulation Support Ring—the Problem (a) and the Solution (b).	13
Figure 5: Vertical Vessel Bottom Support Ring Minimizing Water Accumulation.	13
Figure 6: Vessel-Stiffening Ring Insulation Detail.....	14
Figure 7: Center Nozzle at Top Head of Vessel.	14
Figure 8: Common Nameplate Insulation Detail.	15
Figure 9: Seal-Welded Cap on Insulation for Personnel Protection.	15
Figure 10: Double-Pipe Heat Exchanger Insulation Penetrated by C-Channel Support. .	16
Figure 11: Protrusions Through Jacketing.	16
Figure 12: Pipe Supports Without Protrusions.....	17
Figure 13: Cold Service Pipe Support Without Continuous Vapor Barrier.	18
Figure 14: Cold Service Pipe Support with Continuous Vapor Barrier.	18
Figure 15: Pipe Insulation Penetrated by Column Fireproofing.	19
TABLES	
Table 1: Typical Protective Coating Systems for Austenitic and Duplex Stainless Steels Under Thermal Insulation	22
Table 2: Typical Protective Coating Systems for Carbon Steels Under Thermal Insulation and Fireproofing	25

Section 1: General

1.1 Corrosion under insulation (CUI) has been occurring for as long as hot or cold equipment has been insulated for thermal protection, energy conservation, or process stabilization. The destructive results and nature of the corrosion mechanism were not mentioned in the literature until the 1950s. As more problems have been experienced, concern and interest have built around this subject. Many articles and symposium papers have been published since 1983 as interest and activity in CUI have increased. The increased activity was driven largely by many occurrences of severe CUI resulting in major equipment outages, production losses, and unexpected maintenance costs in refineries, gas plants, and chemical plants.

1.2 To correct these problems, companies have developed their own criteria and approaches to the prevention of CUI. When comparing the various approaches, it is evident that there are many similarities, some differences, some new ideas, and some old ideas that have stood the test of performance. This standard incorporates the experience of many companies throughout the oil, gas, and chemical industries.

1.3 The first ASTM standard relevant to CUI was ASTM C692,¹ adopted in 1971 and originally titled "Evaluating the Influence of Wicking Type Thermal Insulations on the Stress Corrosion Cracking Tendency of Austenitic Stainless Steels."

1.4 A symposium was held jointly by NACE, ASTM, and Materials Technology Institute (MTI)⁽²⁾ on this subject with speakers from industries worldwide in October 1983. The papers were published in 1985 as ASTM Publication STP 880.²

1.5 The first NACE state-of-the-art report on CUI was written in 1989 by Task Group T-6H-31 and issued as NACE Publication 6H189.³ NACE Task Group T-5A-30 was organized shortly thereafter to serve as a forum for further discussion regarding CUI. In addition to reviews of the corrosion mechanisms, perspectives on such CUI topics as methods for mitigation, insulation materials, and inspection were often exchanged. While corrosion engineers were becoming knowledgeable about CUI, ASTM Committee C16 on Thermal Insulation was preparing standards for testing insulation with a propensity to cause chloride stress corrosion cracking (SCC) of austenitic stainless steel. These two groups interacted but proceeded to develop their standards and information separately.

1.6 In this standard, the term *equipment* includes all objects in a facility with external metal surfaces that are insulated or fireproofed and subject to corrosion.

1.7 In previous editions of this standard, carbon steel and austenitic stainless steels were the primary metals addressed. Because of their increased usage in applications where CUI is a concern, duplex stainless steels have been more explicitly addressed in this revision.

1.8 Although most of the attention has been focused on corrosion under thermal insulation, fireproofing materials also function, at least in part, as insulation applied to protect equipment during a potential fire. Other fire protection mechanisms initiated as endothermic reactions within the fireproofing material during a fire are not covered in this standard. Corrosion mechanisms, the root cause of failure, and corrosion prevention are the same for corrosion under fireproofing as for corrosion under insulation.

1.9 Whenever CUI is a consideration, a protective coating or coating system should be applied to the equipment before it is insulated. Protective coatings or coating systems may have service lives that are shorter than the anticipated operational life of the equipment, and thus may require inspection and maintenance to effectively maintain integrity and to minimize the threat of CUI.

⁽²⁾ Materials Technology Institute (MTI), 1215 Fern Ridge Parkway, Suite 206, St. Louis, MO 63141-4405.